



Corporate Headquarters
 CAB Incorporated
 5411 Cole Road Buford, GA USA 30518
 800/241-7311 678/745-2100 Fax 678/745-2082
 www.cabinc.com email: sales@cabinc.com

Texas Manufacturing Facility
 CAB Incorporated
 2306 Rayburn Drive, Nacogdoches, TX USA 75961
 800/435-2643 936/569-9430 Fax 936/569-0795

Common Cast Steel Material Comparison Chart

Specification	Grade or Class	Chemical Composition, max (unless range is given), %																Hardness max, HB	Tensile Properties, min (unless range is given)					Energy Value, ft.lbf								
		C	Si	Mn	S	P	Cu	Ni	Cr	Mo	V	N	Cb/Nb	B	Se	W	Tensile Strength min, Ksi		Yield Point Ksi	Yield Strength Ksi @ 0.2%	Elongation in 2 in, %	Reduction of Area, %	CVN min of 2 and avg of 3 specimens	CVN min for single specimen	Testing Temp., F							
ASTM A27	Carbon Steel	N-1	0.25	0.80	0.75	0.060	0.060																									
		N-2	0.35	0.80	0.60	0.060	0.060																									
		U60-30	0.25	0.80	0.75	0.060	0.060																									
		60-30	0.30	0.80	0.60	0.060	0.060																									
		65-35	0.30	0.80	0.70	0.060	0.060																									
		70-36	0.35	0.80	0.70	0.060	0.060																									
		70-40	0.25	0.80	1.20	0.060	0.060																									
ASTM A128	Manganese Steel	A	11.0 min	1.00			0.070																									
		B-1	11.5-14.0	1.00			0.070																									
		B-2	11.5-14.0	1.00			0.070																									
		B-3	11.5-14.0	1.00			0.070																									
		B-4	11.5-14.0	1.00			0.070																									
		C	11.5-14.0	1.00			0.070			1.5-2.5																						
		D	11.5-14.0	1.00			0.070			3.00-4.00																						
		E-1	11.5-14.0	1.00			0.070						0.90-1.20																			
ASTM A148	Carbon/Alloy Steel	E-2	11.5-14.0	1.00			0.070					1.80-2.10																				
		F	6.0-8.0	1.00			0.070					0.90-1.20																				
		80-40					0.060	0.050												80	40		18	30								
		80-50					0.060	0.050													80	50		22	35							
		90-60					0.060	0.050													90	60		20	40							
		105-85					0.060	0.050													105	85		17	35							
		115-95					0.060	0.050													115	95		14	30							
		130-115					0.060	0.050													130	115		11	25							
		135-125					0.060	0.050													135	125		9	22							
		150-135					0.060	0.050													150	135		7	18							
		160-145					0.060	0.050													160	145		6	12							
		165-150					0.020	0.020													165	150		5	20							
		165-150L					0.020	0.020													165	150		5	20	20	16					
		210-180					0.020	0.020													210	180		4	15							
		210-180L					0.020	0.020													210	180		5	15	15	12					
		260-210					0.020	0.020													260	210		3	6							
		260-210L					0.020	0.020													260	210		3	6	6	4					
ASTM A216	Carbon Steel	WCA	0.25	0.60	0.70	0.045	0.040	0.30	0.50	0.50	0.20	0.03																				
		WCB	0.30	0.60	1.00	0.045	0.040	0.30	0.50	0.50	0.20	0.03																				
		WCC	0.25	0.60	1.20	0.045	0.040	0.30	0.50	0.50	0.20	0.03																				
ASTM A297	Heat Resistant Steel	HF	0.20-0.40	2.00	2.00	0.040	0.040		8-12	18-23	0.50																					
		HH	0.20-0.50	2.00	2.00	0.040	0.040		11-14	24-28	0.50																					
		HI	0.20-0.50	2.00	2.00	0.040	0.040		14-18	26-30	0.50																					
		HK	0.20-0.60	2.00	2.00	0.040	0.040		18-22	24-28	0.50																					
		HE	0.20-0.50	2.00	2.00	0.040	0.040		8-11	26-30	0.50																					
		HT	0.35-0.75	2.50	2.00	0.040	0.040		33-37	15-19	0.50																					
		HU	0.35-0.75	2.50	2.00	0.040	0.040		37-41	17-21	0.50																					
		HW	0.35-0.75	2.50	2.00	0.040	0.040		58-62	10-14	0.50																					
		HX	0.35-0.75	2.50	2.00	0.040	0.040		64-68	15-19	0.50																					
		HC	0.50	2.00	1.00	0.040	0.040		4.00	26-30	0.50																					
		HD	0.50	2.00	1.50	0.040	0.040		4-7	26-30	0.50																					
		HL	0.20-0.60	2.00	2.00	0.040	0.040		18-22	28-32	0.50																					
		HN	0.20-0.50	2.00	2.00	0.040	0.040		23-27	19-23	0.50																					
		HP	0.35-0.75	2.50	2.00	0.040	0.040		33-37	24-28	0.50																					
ASTM A351	Stainless Steel for Pressure-Containing Parts	CF3	0.03	2.00	1.50	0.040	0.040		8-12	17-21	0.50									70		30	35									
		CF3A	0.03	2.00	1.50	0.040	0.040		8-12	17-21	0.50									77		35	35									
		CF8	0.08	2.00	1.50	0.040	0.040		8-11	18-21	0.50									70		30	35									
		CF8A	0.08	2.00	1.50	0.040	0.040		8-11	18-21	0.50										77		35	35								
		CF3M	0.03	1.50	1.50	0.040	0.040		9-13	17-21	2.00-3.00										70		30	30								
		CF3MA	0.03	1.50	1.50	0.040	0.040		9-13	17-21	2.00-3.00										80		37	30								
		CF8M	0.08	1.50	1.50	0.040	0.040		9-12	18-21	2.00-3.00										70		30	30								
		CF3MN	0.03	1.50	1.50	0.040	0.040		9-13	17-21	2.00-3.00		0.10-0.20								75		37	35								
		CF8C	0.08	2.00	1.50	0.040	0.040		9-12	18-21	0.50					1.00					70		30	30								

